

IP SERVICES



Home IP Services PATENTSCOPE®



Search result: 1 of 1

(WO/2002/014322) PORPHYRIN COMPOUNDS CONSISTING OF PORPHYRIN RINGS FUSED IN A SINGLE DIRECTION BY THREE BONDS, I.E., ONE MESO-M F

MESO CARBON BOND AND TWO \$g(b)-\$g(b) CARBON BONDS AND PROCESS FOR THEIR SYNTHESIS	
Biblio. Data Description Claims	National Phase Notices Documents
Latest bibliographic data on file with the	International Bureau
Publication Number: WO/2002/014322	International Application No.: PCT/JP2001/006832

C07D 487/22 (2006.01) Int. Class.:

Applicants: JAPAN SCIENCE AND TECHNOLOGY CORPORATION [JP/JP]; 1-8, Hon-cho 4-chome Kawaguchi-shi

Saitama 332-0012 (JP) (AT, BE, CA, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IL, IT, LU, MC, NL, PT,

08.08.2001

SE, TR only).

21.02.2002

OSUKA, Atsuhiro [JP/JP]; 2-4-6, Oginosato Ohtsu-shi Shiga 529-0246 (JP) (US Only).

International Filing Date:

Inventor:

Title:

Publication Date:

OSUKA, Atsuhiro [JP/JP]; 2-4-6, Oginosato Ohtsu-shi Shiga 529-0246 (JP).

MIYAMOTO, Harumi; Hougaku Bldg. 7F 19-14, Toranomon 1-chome Minato-ku Tokyo 105-0001 (JP). Agent: Priority Data: 2000-243699 11.08.2000 JP

PORPHYRIN COMPOUNDS CONSISTING OF PORPHYRIN RINGS FUSED IN A SINGLE DIRECTION

BY THREE BONDS, I.E., ONE MESO-MESO CARBON BOND AND TWO \$g(b)-\$g(b) CARBON BONDS AND PROCESS FOR THEIR SYNTHESIS

A porphyrin ring-fusion polymer which consists of two or more Zn?II¿-porphyrin Abstract:

rings fused in a single direction and in which any two porphyrin rings adjacent to each other are fused by three covalent bonds, that is, one meso-meso carbon bond (i.e., one bond between meso-position carbon atoms) and two \$g(b)-\$g(b) carbon bonds (i.e., two bonds between \$g(b)-position carbon atoms adjacent to the mesoposition carbon atoms); a process for preparing the porphyrin ring-fusion polymer regioselectively by conducting the fusion reaction in an aromatic hydrocarbon solvent in the presence of a quinone and a Lewis acid containing a rare earth element under reflux; and fused-ring porphyrin compounds obtained by subjecting the prophyrin ring-fusion polymer to demetallization or replacement of the Zn atoms

by other metal atoms.

Designated CA, IL, US.

European Patent Office (EPO) (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, States:

Publication Language:

Japanese (JA)

Filing Language:

Japanese (JA)